

CH1625125G

Electrical Characteristics

Material	Permeability (μ)	AL \pm 8% (nH/N ²)	DCB (% min) @ 20 Oe	Coreloss (mW/cm ² , max) @ 50kHz, 100G
High Flux	125	384	84.64	4

OD : 1625



Core Dimensions

Dimensions		Uncoated		Coated		Color	Packaging
		(mm)	(inch)	(mm)	(inch)		
OD	(Max)	165.00	6.496	167.20	6.583	Black	Box Qty = 4 pcs
ID	(min)	88.90	3.500	86.90	3.421		
HT	(max)	25.40	1.000	27.30	1.075		

Physical Characteristics

Cross Section (A)	Path Length (l)	Window Area (Wa)	Volume (V)	Breakdown Voltage (Vac)
9.460 cm ²	38.65 cm	59.31 cm ²	365.629 cm ³	1,000
1.46630 in ²	15.217 in	11,705,189 cmil	22.3107 in ³	

Winding Information

0% Winding length/turn (cm)		
13.490		
40% winding factor Surface Area (cm ²)		
916.95		
40% Wound Di.(mm)		
OD	ID	HT
188.62	56.89	53.02

Typical DC Bias Performance

